

MATERIAL ABSORBANT ELECTROMAGNETIC FLEXIBIL

Material / Caracteristici	MICRO	FE 300	GR 300	TN 150
Atenuarea max. la grosimea data, dB	10	30	11	9
Frecventa, GHz	2,1	1,9	1,9	2,2
Rezistenta la rupere, KN/m	20	59	61	57
Elongatie, max. %	400			
Uzura, mm ³ /1 kgf		292	263	272
Grosimea de material la masurare, mm	3,6	3	3,5	3,5

Materialul a fost masurat in Laboratorul de Compatibilitate Electromagnetica al INCDIE ICPE-CA.



AVANTAJE

- Material extrem de flexibil;
- Aderenta la diverse suprafete;
- Rezistenta excelenta;
- Disponibil sub diferite grosimi.